

# WOOD SEALANT

## PAINTABLE SEALANT FOR SEALING IN WOOD APPLICATIONS



### PRODUCT DESCRIPTION

High quality sealant for sealing joints and cracks in wood and parquet and laminate flooring. Paintable, varnishable, easy to process.

### FIELD OF APPLICATION

Suitable for sealing of all kinds of seams, joints and gaps around wood, such as connection joints along walls, stairs, radiator pipes, etc., specifically at sites where the application of skirting boards is not possible. Not suitable for bitumen, silicone, polyethylene (PE), polypropylene (PP) and P.T.F.E.

### PROPERTIES

- Paintable
- Can be varnished
- Easy to apply
- Easy to tool
- 10-year warranty
- Plasto-elastic

### PREPARATION

**Working conditions:** Only apply at temperatures between +5°C and +40°C.

**Surface requirements:** The surface must be dry, clean and free of dust, rust and grease.

**Preliminary surface treatment:** For a good result, cover the joint's edges with masking tape. If necessary, prevent three-sided bonding by filling the joint with a foam backer rod or PE film.

**Tools:** Apply cartridge with a Power Pistol. Multi Tool to open the cartridge and tooling the sealant.

### APPLICATION

**Coverage:** Content suitable for approx. 8 to 15 m (depending on the diameter of the joint).

#### Directions for use:

Use sealant gun to handle cartridge. Open the cartridge by cutting off the plastic nipple on the top side at the screw thread with a sharp knife. Screw on the nozzle and chamfer at the desired width. Cut the nipple down till the screw thread. Screw on the plastic nozzle and chamfer at the desired width. Use sealant gun to handle cartridge. Ensure a minimum joint width of 6 mm and a maximum of 24 mm. The depth of the joint must be 6 to 9 mm. Inject the sealant evenly into the joint and tool within 10 minutes with a putty knife or finger. Remove the applied masking tape immediately after tooling.

**Stains/residue:** Remove wet stains immediately with water. Cured sealant residue can only be removed mechanically.

**Points of attention:** The sealant is paintable, varnishable and weather resistant upon complete curing.

### CURE TIMES

**Skin over time:** approx. 15 minutes

**Cure rate:** approx. 1 mm/24 hrs

**Dry/Cure time:** approx. Tack free after 30-60 minutes. Completely dry after 8-14 days, depending on relative air humidity and temperature.

\* Curing time may vary depending on a.o. surface, product quantity used, humidity level and ambient temperature.

### TECHNICAL PROPERTIES

**Moisture resistance:** Good

**Temperature resistance:** From -20°C to +80°C

**UV resistance:** Good

**Mildew resistance:** Nil

**Paintability:** Very good

**Elasticity:** Limited

**Filling capacity:** Good

### TECHNICAL SPECIFICATIONS

**Chemical base:** Acrylic dispersion

**Colour:** Light Oak

**Viscosity:** approx. 0 mPa.s., Pasty

**Solid contents:** approx. 78 %

**Density:** approx. 1.6 g/cm<sup>3</sup>

**Shrinkage:** approx. 35 %

### STORAGE CONDITIONS

At least 24 months after date of manufacture. Limited shelf life after opening. Store in properly sealed packaging in a dry place at between +5°C and +25°C.